

Effect of potentially chromogenic beverages on shear bond strength of acrylic denture teeth to heat-polymerized denture base resins

Karin Hermans Neppelenbroek, Vanessa Migliorini Urban¹, Denise Gusmão de Oliveira, Vinícius Carvalho Porto, Hercules Jorge Almilhatti², Nara Hellen Campanha¹

Department of Prosthodontics, Bauru School of Dentistry, University of São Paulo, Bauru, São Paulo, ¹Department of Dentistry, Ponta Grossa State University, Ponta Grossa, Paraná, ²Department of Restorative Dentistry, Federal University of Paraná, Curitiba, Brazil

Abstract

Background: Detachment of denture acrylic resin artificial teeth from denture base resin is one of the most common problems presented by denture wearers. Purpose: This study investigated the shear bond strength (SBS) and fracture type of bonding interface of two commercial acrylic teeth (Vipi Dent Plus e Biolux) to two denture base resins (Vipi Cril e Lucitone 550) after immersion in potentially chromogenic beverages (coffee, cola soft drink, and red wine) or control solution (distilled water).

Materials and Methods: Maxillary central incisor acrylic teeth were placed at 45° to denture base resin and submitted to short polymerization cycle according to manufacturers. Specimens were divided according to the combination tooth/resin/solution ($n = 8$) and submitted to bond strength tests in a universal testing machine MTS-810 (0.5 mm/min). Subsequently, fracture area was analyzed by stereomicroscope at a magnification of $\times 10$ and categorized into adhesive, cohesive, or mixed failure.

Results: The bond strength of teeth/denture base resins interface was not significantly affected by tested solutions ($P > 0.087$), except for Biolux teeth immersed in coffee ($P < 0.01$). In all conditions, the Vipi Dent Plus teeth showed higher bond strength to Lucitone and Vipi Cril resins when compared to Biolux teeth ($P < 0.003$). All specimens' failure modes were cohesive.

Conclusions: The SBS of acrylic teeth to denture base resins was not generally influenced by immersion in the tested staining beverages.

Key Words: Acrylic resin, bond strength, coloring agents, tooth artificial

Address for correspondence:

Dr. Karin Hermans Neppelenbroek, Al Octávio Pinheiro Brisola, 9-75, Bauru, São Paulo 17012-901, Brazil. E-mail: khnepp@yahoo.com.br

Received: 14th September, 2015, **Accepted:** 07th March, 2016

INTRODUCTION

Since 1940 acrylic resin artificial teeth are used as denture teeth because of their similar characteristics and

chemical bond with denture base resins.^[1,2] However, a detachment of artificial teeth seems to be the main reason of dentures' repair, reaching up to 1/3 of maintenance

This is an open access article distributed under the terms of the Creative Commons Attribution-NonCommercial-ShareAlike 3.0 License, which allows others to remix, tweak, and build upon the work non-commercially, as long as the author is credited and the new creations are licensed under the identical terms.

For reprints contact: reprints@medknow.com

How to cite this article: Neppelenbroek KH, Urban VM, de Oliveira DG, Porto VC, Almilhatti HJ, Campanha NH. Effect of potentially chromogenic beverages on shear bond strength of acrylic denture teeth to heat-polymerized denture base resins. J Indian Prosthodont Soc 2016;16:271-5.

Access this article online	
Quick Response Code:	Website: www.j-ips.org
	DOI: 10.4103/0972-4052.179265

made in these prostheses, usually in the anterior portion of the denture.^[3-7]

Dentures are commonly in contact with saliva or immersed in water or cleansing solutions.^[7-10] Hence, dentures may undergo sorption of liquid such as saliva, cleansing solutions and food within the polymer (absorption), and solubility.^[8-11] The absorbed water can act like a plasticizer and lower the bond between acrylic teeth and the base resins.^[7,12] Therefore, if denture's teeth and base resin can absorb water, they would be able to absorb other liquids, such as potentially chromogenic beverages.

The absorption and adsorption of beverages can lead to polymer outer discoloration because of the mild penetration and reaction of these materials to coloring agents due to plaque accumulation and surface degradation.^[13,14]

Natural and artificial colorants are commonly found in human diet foods. Studies demonstrate that beverages like coffee are chromogenic.^[15,16] It has also been suggested that alcohol drinks such as wine promote softening and degradation of the material's polymeric surface.^[17,18] Moreover, low pH of acidic beverages like cola drinks can also damage the integrity of these materials.^[19,20] Therefore, in addition to staining, certain foods have an influence in other acrylic resin characteristics and might as well interfere on denture base/tooth bonding interface.

Although studies that evaluated bond strength of acrylic teeth and base resins after prolonged immersion in water or after thermal cycling are found in the literature,^[21-23] there are no researches on the effects of immersion in staining beverages on bonded interface. Thus, this study aimed to evaluate the shear bond strength (SBS) of two commercial acrylic teeth and two commercial brands of denture base heat-cured resin after immersion in three potentially chromogenic beverages.

MATERIALS AND METHODS

Specimen preparation

Two commercial acrylic resin artificial teeth (Vipi Dent Plus, Dental Vipi Ltda., Pirassununga, SP, Brazil and Biolux, Dental Vipi Ltda., Pirassununga, SP, Brazil) and two commercial brands of denture base resin (Lucitone 550, Dentsply Ind. E Com. Ltda., Petrópolis, RJ, Brazil and Vipi Cril, Dental Vipi Ltda., Pirassununga, SP, Brazil) were used to manufacture the specimens. Japanese standards for acrylic teeth (JIST 6506, 1989)^[24] were followed and a maxillary incisor acrylic tooth was placed at 45° in a round cardboard container (12.7 mm × 20 mm) filled with modeling wax. Wax blocks patterns were made and conventional

casting was used. Before inserting in the gypsum mold, the denture resin dough manipulated following manufacturers' instructions, the bonding surface of the tooth was pretreated with methyl-methacrylate (MMA) for 180s.^[6,25,26] Denture base resins were polymerized in a water bath according to manufacturers' instructions as well (73°C for 90 min and 100°C for 30 min for Lucitone; and 70°C for 30 min and 100°C for 90 min for Vipi Cril). After deflasking, specimens were immersed in distilled water at 37°C for 48 h for residual monomer release. Thirty-two specimens were made for each tooth/base resin combination.

Solutions preparation

The coffee solution was prepared by adding 2.4 g of instant coffee (Nescafé Tradicão, Nestlé Brazil Ltda., Araras, São Paulo, Brazil) to 200 mL of boiling distilled water. Specimens were immersed only after complete bench cooling of the coffee solution. Red wine (Vinho Tinto Seco Campo Largo, Vinícola Campo Largo, Campo Largo, Paraná, Brazil) was obtained from 750 mL bottles, and cola soft drink (The Coca-Cola Company, Curitiba, Paraná, Brazil) was obtained from 600 mL containers.^[18] Distilled water was the control group solution. Specimens were randomly divided according to acrylic teeth/denture base resins combinations ($n = 8$) and individually immersed in dark vials with 200 mL of tested solutions. Specimens were stored in the vials for 30 days at 37°C to simulate 2.5 years of daily intake of the beverages.^[18,27-29] Solutions were stirred once a day and weekly replaced. Coffee solutions were prepared immediately before weekly replacing, and red wine and soft drink solutions were substituted by solutions in newly opened containers.^[13,16]

Shear bond strength test

After 30 days of storage, specimens were tested by a SBS machine (810, MTS System Corporation, Minnesota, USA) with a loading force at a crosshead speed of 0.5 mm/min until failure.^[2,30] SBS values were calculated using the formula σ (MPa) = F (N)/A (mm²), where F is the maximum breakout force and A is the adhesive area.^[31] Fracture surfaces were analyzed by stereomicroscope (Carl Zeiss, Jena, Alemanha) at ×10 of magnification and categorized into adhesive failure that denotes total separation at the interface between teeth and denture base resin, to cohesive failure that denotes a full break in the denture base resin or artificial tooth, or to mixed failure that denotes both.

Statistical analysis

The data for SBS test were analyzed by using Kruskal–Wallis test ($\alpha = 0.05$). Previously, a Kolmogorov–Smirnov test was carried out to check for homogeneity of data. Failure mode analyses were done by percentage.

RESULTS

SBS mean and standard deviations for all combinations of acrylic teeth/denture base resins and immersion solutions used are summarized in Table I.

Biolux teeth bonded to either denture resins presented lower SBS values when compared do Vipi Dent Plus teeth combinations ($P < 0.003$). Analysis of data also revealed there was no significant variation in SBS of Biolux teeth bonded to both denture resins when immersed in water (control), cola, or red wine ($P > 0.087$). However, when immersed in coffee, Biolux teeth showed a decrease in SBS values when bonded to Lucitone ($P < 0.01$). In addition, Vipi Dent Plus teeth bonded to both denture resins indicated no significant difference ($P < 0.01$) in SBS after immersion in all solutions ($P = 0.223$). Furthermore, visual analysis of the fractures showed that all specimens, including control, resulted in cohesive failure (100%).

DISCUSSION

Denture teeth detachment is one of the most common problems presented by denture wearers.^[2] A number of researches on this subject can be pointed out in the pertinent literature but none of them, at the best of our knowledge, correlates potentially chromogenic beverages and bond strength between acrylic teeth and denture base acrylic resin.

When artificial acrylic teeth are exposed to the oral cavity, they will be in contact with saliva, beverages, and cleaning agents, and such materials are prone to the absorption and adsorption processes.^[8-11] It has been shown that certain kinds of foods that are routinely ingested in a human diet can promote discoloration, surface degradation, and changes in other properties of the polymers.^[13,14] Therefore, this study aimed at investigating the SBS of two different commercial acrylic teeth bonded to two different brands of denture base^[18] resins after immersion in staining beverages. The aqueous solutions used in this study can be absorbed and adsorbed by the teeth, acting as plasticizers.^[7,12] It is known that the composition,

pH, and polarity of the liquid medium to which the polymers are subjected, as well as the immersion time, are factors that can change its solubility and cause polymer degradation.^[13,14] In the present investigation, beverages with natural dyes were used: Red wine, which contains anthocyanin from grape; coffee, which has caramel coloring; and orange juice, which contains annatto. From this, we supposed that the presence of these dyes in beverages probably would have an additional effect on the SBS of artificial teeth bonded to denture base resins in relation to water. However, SBS of teeth/denture base resins interface was not significantly affected by tested solutions, except for Biolux teeth immersed in coffee.

Although different bond strength evaluation methods are described by the international specification, shear seems to have a greater clinical relevance by simulating forces on teeth lingual surfaces and therefore used as the main method by several of authors.^[2,5,6,23,25,32,33] Evaluating different artificial teeth bonded to the same acrylic resin, it can be assumed that the differences in the results are due to the different types of acrylic teeth used in this study. Acrylic resin artificial teeth are composed basically of poly-MMA beads and pigments immersed in a polymeric matrix with cross-linking agents. The chemical bond between teeth and denture base resins results from the propagation of MMA monomer into the artificial tooth.^[34-36] Afterward, a network is made around the polymer beads by the monomer and the cross-linking agent.^[37] Cross-linking agents are added to denture acrylic teeth to improve strength and resistance to wear and to prevent discoloration and crazing.^[38]

In our study, Vipi Dent Plus teeth presented greater SBS results than Biolux teeth in all situations. These results can be explained by the characteristics of the teeth's material. According to the manufacturer, both teeth have in its composition dimethacrylate of polymerized ethylene glycol which is a cross-linking agent. However, Biolux teeth have high molecular weight polymers that provide the possibility of higher content of cross-linking agents and the presence of the double cross-linking system^[39,40] forming a fully interpenetrate polymer chain while Vipi Dent forms only a linear polymer chain.^[41] It seems to be well established that as the cross-linking content of the tooth increases the bonding between it and denture base resins decreases.^[2,7,42,43] This happens due to the enhanced surface features of the high cross-linking acrylic teeth that jeopardize permeation of the denture base resin monomer, forming a weaker interwoven polymer network.

Biolux teeth when combined with Vipi Cril denture resin showed less resistance after immersion in coffee, which was not observed for Vipi Dent Plus teeth. There are no studies up to the present time that evaluate bond strength between acrylic teeth and denture base resins after immersion in potentially

Table 1: Shear bond strength (MPa) mean±standard deviations of the study groups

Solutions	Teeth/resin			
	Mean±SD			
	Biolux/ Lucitone	Biolux/ Vipi Cril	Vipi Dent Plus/Lucitone	Vipi Dent Plus/Vipi Cril
Distilled water	9.66±1.40 ^{Aa}	9.44±1.66 ^{Aa}	15.09±1.89 ^{Ab}	14.97±2.97 ^{Ab}
Coffee	8.40±1.52 ^{Ba}	8.79±1.81 ^{Aa}	14.48±1.83 ^{Ab}	15.58±2.57 ^{Ab}
Cola soft drink	9.61±1.28 ^{Aa}	8.96±0.85 ^{Aa}	15.75±3.18 ^{Ab}	15.06±3.26 ^{Ab}
Red wine	8.93±1.22 ^{Aa}	9.82±1.97 ^{Aa}	15.38±2.57 ^{Ab}	15.19±2.64 ^{Ab}

SBS mean and SD followed by a distinct capital letter in columns and lower case letter in rows are statistically different ($P < 0.05$). SBS: Shear bond strength, SD: Standard deviation

staining solutions. Thus, only indirect comparisons between other studies and ours can be established. Ruyter *et al.*^[44] stated that the polarity degree of the staining agent defines the penetration degree into resin's bulk. The less polar beverages, such as coffee, can penetrate easier and join the polymer matrix.^[45] Several authors observed color modification in acrylic resins after prolonged immersion in coffee.^[46,47] It was also shown that coffee causes a significant change in color stability of acrylic resin artificial tooth.^[16,45] The polymers' surface degradation caused by coffee may be related to its affinity with these materials and to adsorption and absorption of its colorants, particularly of the yellow one.^[27,48] The tannic acid present in solutions like tea and coffee can also promote this surface alteration.^[27,46,49] Khan *et al.*^[49] reported that extended immersion in tea solution worsened the features of light-curing acrylic resin denture base, such as water absorption, flexural strength, and hardness. Therefore, the bond strength reduction perceived on Biolux teeth after immersion in coffee solution in the present study can be attributed to the solution's low polarity, its high affinity to the polymer, and the presence of yellow dye and tannic acid in its composition.

In our investigation, the failure modes were cohesive for all specimens, consistent to the results of similar studies.^[21,23,50] However, Akin *et al.*^[31] reported 93% of adhesive failures, when evaluating acrylic tooth bonded to denture base resin. This outcome may be due to the lack of tooth bonding surface treatment in this study. In our study, the tooth ridge lap was treated with MMA monomer that is proven to increase SBS and lead to most reliable results, regarding failure modes.^[21,35,51] Cohesive failures happen more often than adhesive failures when the bond interfaces are not contaminated.^[52]

Overall, this study suggests that potentially chromogenic beverages commonly consumed in daily diet do not cause significant changes in the bond strength between acrylic artificial teeth and heat-polymerized resins used in this study. Moreover, acrylic teeth with higher molecular weight and cross-linking agents have weaker bond compared to those with a lower content of molecular weight and cross-linking agents. However, artificial teeth may undergo several other events that could not be assessed within this study's *in vitro* methodology. In clinical use, acrylic resin artificial teeth can have their surface features influenced by various dynamic conditions, such as quantity and quality of saliva, cleansing procedures, type of feeding (consistency of food), intake frequency of coloring and/or acidic foods, parafunctional habits, accidents/trauma, antagonist teeth, occlusal condition, and among many others. In addition, other aspects are proven to reduce bonding between acrylic teeth and denture base resin, such as contamination in the tooth-denture base resin interface and difference in the structure of the two materials due to their different processing

routes.^[27,53] Furthermore, only two brands of acrylic teeth, two brands of denture heat-polymerized resin, and three types of potentially chromogenic beverages were tested given the many types commercially available. Therefore, the results of this study should be interpreted with caution.

CONCLUSIONS

Within the limits of the study, the following conclusions were drawn:

- SBS between Vipi Dent Plus teeth and Vipi Cril and Lucitone base resins were higher when compared to Biolux teeth bonded to both base resins, regardless of immersion solution
- Staining beverages did not show the impact on SBS in all combinations of teeth/denture base resin, except for Biolux/Lucitone after immersion in coffee solution.

Acknowledgment

Supported by the São Paulo Research Foundation-FAPESP (Grant 2010/07788-4).

Financial support and sponsorship

Nil.

Conflicts of interest

There are no conflicts of interest.

REFERENCES

1. Kelly EB. Has the advent of plastics in dentistry proved of great scientific value? *J Prosthet Dent* 1951;1:168-76.
2. Patil SB, Naveen BH, Patil NP. Bonding acrylic teeth to acrylic resin denture bases: A review. *Gerodontology* 2006;23:131-9.
3. Chai J, Takahashi Y, Takahashi T, Habu T. Bonding durability of conventional resinous denture teeth and highly crosslinked denture teeth to a pour-type denture base resin. *Int J Prosthodont* 2000;13:112-6.
4. Cunningham JL. Bond strength of denture teeth to acrylic bases. *J Dent* 1993;21:274-80.
5. Cunningham JL. Shear bond strength of resin teeth to heat-cured and light-cured denture base resin. *J Oral Rehabil* 2000;27:312-6.
6. Papazoglou E, Vasilas AI. Shear bond strengths for composite and autopolymerized acrylic resins bonded to acrylic resin denture teeth. *J Prosthet Dent* 1999;82:573-8.
7. Takahashi Y, Chai J, Takahashi T, Habu T. Bond strength of denture teeth to denture base resins. *Int J Prosthodont* 2000;13:59-65.
8. Polyzois GL, Yannikakis SA, Zissis AJ, Demetriou PP. Color changes of denture base materials after disinfection and sterilization immersion. *Int J Prosthodont* 1997;10:83-9.
9. Satoh Y, Nagai E, Azaki M, Morikawa M, Ohyama T, Toyoma H, *et al.* Study on high-strength plastic teeth. Tooth discoloration. *J Nihon Univ Sch Dent* 1993;35:192-9.
10. Wong DM, Cheng LY, Chow TW, Clark RK. Effect of processing method on the dimensional accuracy and water sorption of acrylic resin dentures. *J Prosthet Dent* 1999;81:300-4.
11. Hersek N, Canay S, Uzun G, Yildiz F. Color stability of denture base acrylic resins in three food colorants. *J Prosthet Dent* 1999;81:375-9.
12. Aydin AK, Terzioğlu H, Akinay AE, Ulubayram K, Hasirci N. Bond strength and failure analysis of lining materials to denture resin. *Dent Mater* 1999;15:211-8.

13. Ghahramanloo A, Madani AS, Sohrabi K, Sabzevari S. An evaluation of color stability of reinforced composite resin compared with dental porcelain in commonly consumed beverages. *J Calif Dent Assoc* 2008;36:673-80.
14. Horsted-Bindslev P, Mjor IA. *Dentística Operatória Moderna*. 3rd ed. São Paulo: Santos; 1999.
15. Koksall T, Dikbas I. Color stability of different denture teeth materials against various staining agents. *Dent Mater J* 2008;27:139-44.
16. Mutlu-Sagesen L, Ergün G, Ozkan Y, Bek B. Color stability of different denture teeth materials: An *in vitro* study. *J Oral Sci* 2001;43:193-205.
17. Patel SB, Gordan VV, Barrett AA, Shen C. The effect of surface finishing and storage solutions on the color stability of resin-based composites. *J Am Dent Assoc* 2004;135:587-94.
18. Sepúlveda-Navarro WF, Arana-Correa BE, Borges CP, Jorge JH, Urban VM, Campanha NH. Color stability of resins and nylon as denture base material in beverages. *J Prosthodont* 2011;20:632-8.
19. Kurtulmus H, Kumbuloglu O, Aktas RT, Kurtulmus A, Boyacioglu H, Oral O, *et al.* Effects of saliva and nasal secretion on some physical properties of four different resin materials. *Med Oral Patol Oral Cir Bucal* 2010;15:e969-75.
20. Gupta R, Parkash H, Shah N, Jain V. A spectrophotometric evaluation of color changes of various tooth colored veneering materials after exposure to commonly consumed beverages. *J Indian Prosthodont Soc* 2005;5:72-8.
21. Palitsch A, Hannig M, Ferger P, Balkenhol M. Bonding of acrylic denture teeth to MMA/PMMA and light-curing denture base materials: The role of conditioning liquids. *J Dent* 2012;40:210-21.
22. Barbosa DB, Barão VA, Monteiro DR, Compagnoni MA, Marra J. Bond strength of denture teeth to acrylic resin: Effect of thermocycling and polymerisation methods. *Gerodontology* 2008;25:237-44.
23. Chittaranjan B, Taruna M, Sudheer N, Patil NS. Evaluation of shear bond strength of three different types of artificial teeth to heat cure denture base resin: An *in vitro* study. *Indian J Dent Res* 2013;24:321-5.
24. JIST. Japan Science and Technology Agency: Specification 6506: Acrylic resin teeth. Tokyo: JIST; 1989.
25. Barbosa DB, Monteiro DR, Barão VA, Pero AC, Compagnoni MA. Effect of monomer treatment and polymerisation methods on the bond strength of resin teeth to denture base material. *Gerodontology* 2009;26:225-31.
26. Leles CR, Machado AL, Vergani CE, Giampaolo ET, Pavarina AC. Bonding strength between a hard chairside relined resin and a denture base material as influenced by surface treatment. *J Oral Rehabil* 2001;28:1153-7.
27. Guler AU, Yilmaz F, Kulunk T, Guler E, Kurt S. Effects of different drinks on stainability of resin composite provisional restorative materials. *J Prosthet Dent* 2005;94:118-24.
28. Arana-Correa BE, Sepúlveda-Navarro WF, Florez FL, Urban VM, Jorge JH, Campanha NH. Colour stability of acrylic resin denture teeth after immersion in different beverages. *Eur J Prosthodont Restor Dent* 2014;22:56-61.
29. Neppelenbroek KH, Kuroishi E, Hotta J, Marques VR, Moffa EB, Soares S, *et al.* Surface properties of multilayered, acrylic resin artificial teeth after immersion in staining beverages. *J Appl Oral Sci* 2015;23:376-82.
30. Meloto CB, Silva-Concilio LR, Rodrigues-Garciai RC, Canales GT, Rizzatti-Barbosa CM. Effect of surface treatments on the bond strength of different resin teeth to complete denture base material. *Acta Odontol Latinoam* 2013;26:37-42.
31. Akin H, Tugut F, Guney U, Akar T. Shear bond strength of denture teeth to two chemically different denture base resins after various surface treatments. *J Prosthodont* 2014;23:152-6.
32. Geerts GA, Jooste CH. A comparison of the bond strengths of microwave- and water bath-cured denture material. *J Prosthet Dent* 1993;70:406-9.
33. Yanikoglu DN, Duymus DZ, Bayindir DF. Comparative bond strengths of autopolymerising denture resin and light cured composite resin to denture teeth. *Int Dent J* 2002;52:20-4.
34. Adeyemi AA, Lyons MF, Cameron DA. The acrylic tooth-denture base bond: Effect of mechanical preparation and surface treatment. *Eur J Prosthodont Restor Dent* 2007;15:108-14.
35. Chung RW, Clark RK, Darvell BW. The bonding of cold-cured acrylic resin to acrylic denture teeth. *Aust Dent J* 1995;40:241-5.
36. Schneider RL, Curtis ER, Clancy JM. Tensile bond strength of acrylic resin denture teeth to a microwave- or heat-processed denture base. *J Prosthet Dent* 2002;88:145-50.
37. Vallittu PK, Ruyter IE, Nat R. The swelling phenomenon of acrylic resin polymer teeth at the interface with denture base polymers. *J Prosthet Dent* 1997;78:194-9.
38. Powers JM, Sakaguchi RL. *Craig's Restorative Dental Materials*. 13th ed. St.Louis: Mosby Elsevier; 2012.
39. Ogle RE, David LJ, Ortman HR. Clinical wear study of a new tooth material: Part II. *J Prosthet Dent* 1985;54:67-75.
40. Coffey JP, Goodkind RJ, DeLong R, Douglas WH. *In vitro* study of the wear characteristics of natural and artificial teeth. *J Prosthet Dent* 1985;54:273-80.
41. Pisani MX, Macedo AP, Paranhos Hde F, Silva CH. Effect of experimental *Ricinus communis* solution for denture cleaning on the properties of acrylic resin teeth. *Braz Dent J* 2012;23:15-21.
42. Suzuki S, Sakoh M, Shiba A. Adhesive bonding of denture base resins to plastic denture teeth. *J Biomed Mater Res* 1990;24:1091-103.
43. Amin WM. Durability of acrylic tooth bond to polymeric denture base resins. *Eur J Prosthodont Restor Dent* 2002;10:57-61.
44. Ruyter IE, Nilner K, Moller B. Color stability of dental composite resin materials for crown and bridge veneers. *Dent Mater* 1987;3:246-51.
45. Singh SV, Aggarwal P. Effect of tea, coffee and turmeric solutions on the colour of denture base acrylic resin: An *in vitro* study. *J Indian Prosthodont Soc* 2012;12:149-53.
46. Buyukyilmaz S, Ruyter IE. Color stability of denture base polymers. *Int J Prosthodont* 1994;7:372-82.
47. Lai YL, Lui HF, Lee SY. *In vitro* color stability, stain resistance, and water sorption of four removable gingival flange materials. *J Prosthet Dent* 2003;90:293-300.
48. Um CM, Ruyter IE. Staining of resin-based veneering materials with coffee and tea. *Quintessence Int* 1991;22:377-86.
49. Khan Z, von Fraunhofer JA, Razavi R. The staining characteristics, transverse strength, and microhardness of a visible light-cured denture base material. *J Prosthet Dent* 1987;57:384-6.
50. Thean HP, Chew CL, Goh KI. Shear bond strength of denture teeth to base: A comparative study. *Quintessence Int* 1996;27:425-8.
51. Vallittu PK. Bonding of resin teeth to the polymethyl methacrylate denture base material. *Acta Odontol Scand* 1995;53:99-104.
52. Bhaskaran S, Hallikerimath RB. An investigation on the influence of tin foil substitute contamination on bond strength between resin denture teeth and the denture base: An *in vitro* study. *Indian J Dent Res* 2012;23:556.
53. Darbar UR, Huggett R, Harrison A, Williams K. The effect of impurities on the stress distribution at the tooth/denture base resin interface. *Asian J Aesthet Dent* 1994;2:7-10.